

UNITED STATES PATENT AND TRADEMARK OFFICE

I, Charles Edward SITCH BA,

Managing Director of RWS Group Ltd UK Translation Division, of Europa House, Marsham Way, Gerrards Cross, Buckinghamshire, England declare;

1. That I am a citizen of the United Kingdom of Great Britain and Northern Ireland.
2. That the translator responsible for the attached translation is well acquainted with the German and English languages.
3. That the attached is, to the best of RWS Group Ltd knowledge and belief, a true translation into the English language of the accompanying copy of the specification filed with the application for a patent in Germany on 27 August 2003 under the number 103 39 802.3 and the official certificate attached thereto.
4. That I believe that all statements made herein of my own knowledge are true and that all statements made on information and belief are true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the patent application in the United States of America or any patent issuing thereon.



For and on behalf of RWS Group Ltd

The 16th day of January 2009

# FEDERAL REPUBLIC OF GERMANY



## Priority Certificate for the filing of a Patent Application

**File Reference:** 103 39 802.3

**Filing date:** 27 August 2003

**Applicant/Proprietor:** Kalle GmbH & Co KG, 65203 Wiesbaden/DE

**Title:** Intrinsically stable shirred stick consisting of a tubular food casing based on synthetic polymers and the use thereof

**IPC:** A 22 C, C 08 J, C 08 L

The attached documents are a correct and accurate reproduction of the original submission for this application.

Munich, 7 June 2004  
German Patent and Trademark Office  
The President  
pp

[seal of the  
German  
Patent and  
Trademark Office]

[signature]  
Wehner

03/071K

- 1 -

August 27, 2003

Dr. P.-wf

Intrinsically stable shirred stick consisting of a tubular food casing based on synthetic polymers and the use thereof

5 The invention relates to an intrinsically stable shirred tubular food casing, and also to the use of the shirred casing on fully automatic stuffing apparatuses, in particular automatic sausage stuffing and clipping devices or twisting apparatuses.

10

Food casings, especially sausage casings, are predominantly offered in shirred form. In each case about 10 to 200 m of the casing are shirred to form a 5 to 200 cm long stick. Shirring artificial sausage skin  
15 has long been known and numerously described. On an industrial scale, shirring is performed using special machines. The casing which is delivered as roll product is taken off from the roll, inflated and pulled onto the shirring mandrel of the shirring machine. The outer  
20 diameter of the shirring mandrel determines the inner diameter of the stick to be produced. Shirring is a high stress load for the casing. Thus, too high a shirring ratio frequently leads to damage of the casing. To make the casing more supple and to reduce  
25 the mechanical friction load of the shirring systems, it is therefore customarily sprayed or wetted, immediately before shirring, or during shirring, from the inside, from the outside, or from both sides, with water, oil or an oil-in-water emulsion. This measure  
30 further prevents cracks or damage occurring at the pleats forming during shirring. The food casings thus produced are predominantly provided after the shirring

process with a net-type or reinforcing packaging, so that the casings can be handled in the further processing procedure.

5 Cellulose-based food casings shirred in this manner have already been known for a long time. They may also be shirred in such a manner that intrinsically stable sticks are formed which are suitable for fully automatic further processing (DE-A 100 09 979). The  
10 casings are used in particular as peelable skin, for example in the production of small sausages. Cellulose skins are always shirred in the moist state. After the stick has been pulled off the shirring rod, a dimensionally stable or self-supporting shirred stick  
15 is present. After the moisture has dried off, the shirred profile can then be set.

Shirred sticks made of tubular polymer-based food casings are also known. These shirred sticks, however,  
20 are generally not very stable without net-type or reinforcing packaging (see G. Effenberger, Wursthüllen - Kunstdarm [Sausage casings, artificial sausage skin], 2nd Edition [1991] pp. 58-60). In order to be able to ensure the dimensional stability of these shirred  
25 sticks, these food casings, after the shirring process, are given a reinforcing packaging. The different embodiments can comprise, e.g. shirring sleeves, tubing or net-type packaging. For transport, the shirred sticks with or without shirring sleeve are  
30 generally enclosed by a pouch or a tubular net. The shirring pleats of the polymer-based casings show a relatively high resilience, which leads to the fact that the shirred sticks without reinforcing packaging

do not retain their original shape, but expand again. As a result, the mechanical intrinsic stability of the casings decreases, however, so that they can no longer be used on fully automatic stuffing apparatuses.

5 Frequently, the skin shirred onto a sleeve is therefore fixed using limiting disks. The previously known shirred sticks, at least those without shirring sleeve, must therefore be opened either by hand or at least pushed onto the stuffing horn by hand, and then freed

10 again from the respective reinforcing packaging which makes fully automatic operation impossible.

DE-A 196 25 094 A1 (US-A 5 928 738) discloses a biaxially stretch-oriented and heatset single-layer or

15 multilayer stick form polyamide-based packaging casing which has a shirring density of up to 1:200 at a length of the shirred stick of 40 to 100 cm, and also a method for producing such a packaging casing. The wall thickness of the packaging casing is in a range from 10

20 to 50  $\mu\text{m}$ . Before this packaging casing is shirred, a spray solution is applied, which spray solution contains, as shirring lubricant, an emulsifier, paraffin oil or similarly active agent.

25 Shirred sticks having a compression ratio of up to about 150 made of an at least three-layer tubular casing are disclosed by EP-A 1 013 173. The casing has one polyamide layer each on the inside and outside. Between these layers is situated a water vapor-barrier

30 layer, for example based on polyolefin. The casings, before shirring, are sprayed on the outside with water which can additionally contain a fungicide or preservative, and then stored in a water vapor-tight

packaging, so that the water can migrate into the external polyamide layer. It is premoistening which permits the shirring with said high compression ratio.

5 In the older application, which was unpublished at the priority of the present application, EP-A 1 338 204, a packaging casing is disclosed which is shirred at a shirring ratio of 1:200 or higher. The high shirring ratio is achieved by the surface of the casing and that  
10 of the shirred stick together having a mean surface roughness of 0.5 to 5.0  $\mu\text{m}$ . This achieves the shirred stick being able to be taken off from the shirring rod without damage. Preferably, here also, the casing is sprayed before shirring with a solution which comprises  
15 a shirring lubricant.

In the abovementioned documents, shirred sticks having high compression rates are described. Still-present resilience of the shirring pleats, the shirred sticks,  
20 however, are not intrinsically stable and are therefore customarily provided with a reinforcing packaging.

The object was therefore still to provide a shirred stick made of a tubular polymer-based food casing which  
25 does not require additional reinforcing packaging of the previously known sticks and which can be further processed without problems on fully automatic stuffing apparatuses. The shirred stick, without shirring sleeve or other separate support, is to be so stable and  
30 retain a substantially straight shape that it can be taken from a transport container and, e.g., can be placed into the storage vessel (hopper) of the stuffing machine, in which the stick is fully automatically fed

to the stuffing horn.

It has been found that tubular casings based on synthetic polymers can also be shirred to form  
5 intrinsically stable sticks if they experience, enough compression of the shirring operation in the shirring pleating, sufficient folding stress which does not recover. Surprisingly, it has been found, that also thick-walled casings having non-elastic characteristics  
10 develop this intrinsic stability if, in the compressed state, they are set for a period (up to 24 hours). This setting can be carried out, for example, via a reinforcing packaging or storage under vacuum in a close-fitting, air-tight film packaging. In this time,  
15 owing to the setting of the shirring pleats, the tension or the resilience recedes completely. The breakdown of this resilience in particularly thin and soft or elastic materials at the same time as the compression in the currently customary and employed  
20 shirring processes is likewise surprising. Furthermore, it has been found that particularly high insensitivity to bending and folding stress can be achieved by a targeted shirring pleating. In this case, the contact surface area and frictional surface area enlargement of  
25 the shirring pleats among one another is of particular importance. This contact surface area enlargement can be achieved, in particular, via overlapping shirring, as achieved in an ideal manner by a screw shirring method. In addition, it has been found that the  
30 intrinsic stability of the shirred stick can be still further increased by an adhesion-promoting treatment or impregnation of the casing surface, for example by an oil or water film. This may also be achieved by a

corona treatment. In the shirred sticks, the casing exhibits only very low resilience, or none at all, so that the pleats formed on shirring can no longer open. The shirred pleats retain rather their shape once  
5 achieved.

The present invention therefore relates to an intrinsically stable shirred tubular single-layer or multilayer food casing which essentially consists of  
10 synthetic polymers and, without net-type or reinforcing packaging, has sufficient intrinsic stability to be processed on fully automatic stuffing machines. The casing is preferably compressed in a ratio of 100:1 or more.

15 In a preferred embodiment, the sigma-5 value (longitudinal/transverse, measured wet) is below 20/20 N/mm<sup>2</sup>, particularly preferably in the range from 2/2 to 10/10 N/mm<sup>2</sup>.

20 The low resilience or the absence of resilience can be recognized from the fact that the casing, after shirring, extends in the longitudinal direction by no more than 15 %, preferably by no more than 10 %, particularly preferably by no more than 5 %, when it is  
25 stored on a smooth, planar support, usually on a glass plate, without net-type or film packaging or the like, at room temperature (i.e. 23 °C) and 60 % relative humidity (rh).

30 The mechanical stability of the inventive shirred stick is demonstrated, for example, in the fact that it bends under the effect of its own weight by no more than 20



%, preferably by no more than 5 %, based on the length between two support points, (storage at room temperature and 60 % rh). A correspondingly long stick which is mounted on two support points which lie 30 cm apart therefore bends under said conditions by no more than 6 cm, preferably by no more than 1.5 cm. A shirred stick which is stable in such a manner meets the conditions for fully automatic processing.

10 The inventive casing is preferably single-layered. It generally has a wall thickness of no more than 90  $\mu\text{m}$ , particularly preferably from 15 to 30  $\mu\text{m}$ . The casing is generally shirred in a ratio of 100:1 or more, i.e. for example 50 m of the casing give a shirred stick of at  
15 most 50 cm in length (= compression ratio of at least 100:1). Preferably, the compression ratio is even higher still, for instance in the range from 120:1 to 500:1. Methods and apparatuses used for producing the shirred sticks having such a high compression ratio are  
20 disclosed, for example, in EP-A 1 338 204 which was unpublished at the priority of the present application.

An important constituent of the casing is preferably "soft" synthetic polymers or polymer mixtures. To these  
25 belong aliphatic polyamides and aliphatic copolyamides such as nylon 6/66 (obtainable, for example, under the name ®Ulramid C4 from BASF AG) or nylon 6/12 (obtainable, for example, under the names ®Grilon CF6S or ®Grilon BM 13 from Ems Chemie AG), polyether block  
30 amides (e.g. ®Grilon FE 7012 or ®Pebax MH 1657 from Elf Atochem S.A.). In combination with other polymers, the casing can also comprise water-soluble polymers, such as polyvinylpyrrolidone or partially or completely

saponified polyvinylacetate. Suitable polymers are also ionomers, such as ethylene/(meth)acrylic acid copolymers, or (meth)acrylic ester polymers (especially ethylene/methyl acrylate copolymers, ethylene/ethyl acrylate copolymers or ethylene/butyl acrylate copolymers). Further suitable polymers for the inventive casing are polyurethanes (e.g. ®Irogran VP 456/40), copolyesters (e.g. ®Arnitel PM 381 or PM 581) and biodegradable polyesters (e.g. ®Ecoflex).

10

Alternatively, or in addition, the required soft quality of the casing can also be achieved by adding monomeric plasticizers. These are, for example, dimethylsulfoxide (DMSO), butane-1,3-diol, glycerol, water, ethylene glycol, propylene glycol, butylene glycol, diglyceride, diglycol ether, formamide, N-methylformamide, N,N-dimethylformamide (DMF), N,N-dimethylurea, N,N-dimethylacetamide, polyalkylene oxide, glycerol mono-, di- or triacetate, sorbitol, erythritol, mannitol, gluconic acid, galacturonic acid, glucaric acid, glucuronic acid, polyhydroxycarboxylic acids, glucose, fructose, sucrose, citric acid and citric acid derivatives and also any desired mixtures thereof. Some of said plasticizers can also be applied to the already fabricated food casing. For example, the casing can be passed through an aqueous plasticizer bath which contains glycerol.

In a particular embodiment, the adhesion of the individual shirred pleats to one another is increased, for example by a corona treatment. The surface tension after this treatment is expediently 40 to 50 mN/m, preferably 50 to 70 mN/m.

The casing preferably has a nominal caliber of no more than 40 mm. It is thus suitable in particular for use as peeling skin. However, polymer casings having a  
5 greater caliber can also be processed to form intrinsically stable sticks.

The water vapor permeability of the casing is essentially determined by type and fraction of the  
10 synthetic polymers used. Generally, the water vapor permeability is 5 to 1000 g/m<sup>2</sup> d, preferably 20 to 400 g/m<sup>2</sup> d, particularly preferably 50 to 200 g/m<sup>2</sup> d, determined as specified in DIN 53 122 at 23 °C.

15 Expediently, the shirred food casing is closed at one end, for example by a metal or plastic clip. The closure at one end can also be performed by twisting the casing itself or by welding or gluing.

20 Shirring machines and shirring apparatuses for producing the inventive intrinsically stable shirred casing are known and are described, for example, in the abovementioned EP-A 1 338 204. The shirring elements form, for example, a spiral, axial or screw system.  
25 They lead to the formation of shirred pleats which are essentially directed perpendicular to the machine direction, or of those which are at an incline and substantially overlap one another. Shirred sticks having the last-mentioned pleat structure are generally  
30 preferred. They may be produced particularly expediently using a screw system.

If appropriate, before the shirring or during the

shirring, a shirring lubricant is applied to the tubular casing. Expediently, this agent is sprayed onto the inside and/or the outside. A particularly suitable shirring lubricant is, for example, paraffin oil. Depending on the type of the casing, it can also be employed in the form of an oil-in-water emulsion. An impregnation can also be applied to the inside of the casing, which impregnation specifically controls the sausage emulsion adhesion and e.g. improves the peeling of the casing.

By means of a temporary setting of the shirring geometry and the resultant breakdown in tension of the shirred pleats, the required intrinsic stability of the stick is achieved.

The example hereinafter serves to illustrate the invention.

#### 20 Example

A single-layered soft smokeable polymer casing made of 20 % by weight polyether block amide, 20 % by weight polyvinyl alcohol and 60 % by weight nylon 6/66 having a  $\sigma_s$  value of 2/2 N/mm<sup>2</sup> (longitudinal/transverse) and a water vapor permeability of 200 g/m<sup>2</sup> d (determined as specified in DIN 53 122 at 23 °C; moisture gradient 85 %/0 % rh) was premoistened with water on a rewinder. In each case 24.4 m of the casing were then shirred on a shirring machine having an axial shirring system to give an intrinsically stable stick of 17.5 cm in length. During the shirring operation, the outside of the casing was sprayed with paraffin oil. An impregnation to improve the peeling properties was

sprayed onto the inside (via a shirring mandrel equipped with spray nozzles). A plurality of the sticks were packed into a pouch using an automatic packing system and welded under vacuum.

5

The sticks were then removed from the pouch and placed into the feed hopper of a fast-running stuffing machine (Frank-A-Matic), from where they were fully automatically fed to the stuffing horn. In this manner,  
10 up to 2 tons of sausage emulsion could be processed per hour to small sausages of a caliber of 24 mm. Subsequently, the small sausages, as customary, were smoked and cooked. After cooling, the casing was peeled off on an automatic unit; the then casing-less small  
15 sausages were then placed in glass jars and sealed.

An equally long (17.5 cm) stick of a cellulose-based peeling skin comprises, in contrast, generally only 12.19 m of tubular casing. By means of the inventive  
20 shirred stick, the stuffing performance could therefore be increased by 25 %.

In addition, the invention relates to the use of the shirred food casing on a fully automatic stuffing  
25 apparatus, preferably on fully automatic sausage stuffing, portioning, clipping and twisting apparatuses.

Patent claims

1. An intrinsically stable shirred tubular single-layer or multilayer food casing, which essentially consists of synthetic polymers and has, without a net or reinforcing packaging, sufficient intrinsic stability to be able to be processed on fully automatic stuffing machines.
2. The shirred food casing as claimed in claim 1, wherein it is compressed in a ratio of 100:1 or more, preferably 120:1 to 500:1.
3. The shirred food casing as claimed in claim 1 or 2, wherein it has a sigma-5 value (longitudinal/transverse, measured wet) of less than 20/20 N/mm<sup>2</sup>, preferably a sigma- % value in the range from 2/2 to 10/10 N/mm<sup>2</sup>.
4. The shirred food casing as claimed in one or more of claims 1 to 3, wherein, after shirring, it extends in the longitudinal direction by no more than 15 %, preferably by no more than 10 %, particularly preferably by no more than 5 %, when it is stored on a smooth planar support at room temperature and 60 % rh.
5. The shirred food casing as claimed in one or more of claims 1 to 4, wherein it bends under the effect of its own weight by no more than 20 %, preferably by no more than 5 %, based on the length between two support points, at room

temperature.

6. The shirred food casing as claimed in one or more of claims 1 to 5, wherein it is single-layered.
7. The shirred food casing as claimed in one or more of claims 1 to 6, wherein it has a wall thickness of no more than 90  $\mu\text{m}$ , particularly preferably from 15 to 30  $\mu\text{m}$ .
8. The shirred food casing as claimed in one or more of claims 1 to 7, wherein it contains soft synthetic polymers or polymer mixtures, preferably aliphatic polyamides, or aliphatic copolyamides, or polyether block amides.
9. The shirred food casing as claimed in one or more of claims 1 to 8, wherein it is plasticized by at least one monomeric plasticizer, preferably by dimethylsulfoxide, butane-1,3-diol, glycerol, water, ethylene glycol, propylene glycol, butylene glycol, diglyceride, diglycol ether, formamide, N-methylformamide, N,N-dimethylformamide, N,N-dimethylurea, N,N-dimethylacetamide, polyalkylene oxide, glycerol mono-, di- or triacetate, sorbitol, erythritol, mannitol, gluconic acid, galacturonic acid, glucaric acid, glucuronic acid, polyhydroxycarboxylic acids, glucose, fructose, sucrose, citric acid or a citric acid derivative, or any desired mixture thereof.
10. The shirred food casing as claimed in one or more of claims 1 to 9, wherein it has a nominal caliber

of no more than 40 mm.

11. The shirred food casing as claimed in one or more  
of claims 1 to 10, wherein the casing has a water  
5 vapor permeability of 5 to 1000 g/m<sup>2</sup> d, preferably  
20 to 400 g/m<sup>2</sup> d, particularly preferably 50 to  
200 g/m<sup>2</sup> d, determined as specified in DIN 53 122  
at 23 °C.
- 10 12. The shirred food casing as claimed in one or more  
of claims 1 to 11, wherein the casing is corona-  
treated on the outside.
13. The shirred food casing as claimed in one or more  
15 of claims 1 to 12, wherein it is closed at one  
end, preferably by twisting, welding, gluing or by  
a metal or plastic clip.
14. The shirred food casing as claimed in one or more  
20 of claims 1 to 13, wherein the casing is permeable  
to cold smoke, warm smoke, or hot smoke.
15. The shirred food casing as claimed in one or more  
of claims 1 to 14, wherein it achieves the  
25 required intrinsic stability by a temporary  
setting of the shirring geometry and the resultant  
breakdown in tension of the shirred pleats.
16. The use of the shirred food casing as claimed in  
30 one or more of claims 1 to 15 on a fully automatic  
stuffing apparatus, preferably on fully automatic  
sausage stuffing, portioning, clipping and  
twisting apparatuses.



Abstract:

Intrinsically stable shirred stick consisting of a  
tubular food casing based on synthetic polymers and the  
5 use thereof

Disclosed is an intrinsically stable shirred, tubular,  
single-layer or multilayer food casing that preferably  
has a sigma-5 value (longitudinal/transversal, measured  
10 in a moist state) of less than 20/20 N/mm<sup>2</sup>. Said casing  
is preferably shirred at a ratio of 100:1 or more,  
preferably 120:1 to 500:1, and is essentially made of  
synthetic polymers. The shirred casing can be stored  
and transported without using a net-type envelope and  
15 is particularly suitable for processing on fully  
automatic sausage stuffing, portioning, clipping, and  
twisting devices.